

Fabric Specification Sheet

4-Ply 17oz Wideshade IV Ultra Style:

Available Widths: 120"

(305cm)

Roll Lengths: 25 yard standard

(23 m)

Shipping: Rolls shipped on 3" (7.62 cm) ID paper core

Construction: 4 ply laminate (70% Vinyl and 30% Fiberglass)

(Each vinyl is equal thickness and weight)

Surface Texture: As Laminated – Various embossing patterns available

Thread Count: 68 threads per square inch

(23 per square cm)

Weight: 17.9 oz per square yard (+ or - 2.0)

> (606 grams per square meter) (+ or - 68)

Thickness: 16.9 mil (+ or - 2.0)

(+ or - .05) (.42 mm)

Instron Warp Fill Tear Strength: 9 Lbs/In 10 Lbs/In

Instron Warp Fill

Breaking Strength: 339 Lbs/In 256 Lbs/In

Opacity: Blackout

Visual check

Washability: Material may be dusted with a damp cloth. When scrubbing is necessary, warm

water, mild detergents and gentle rubbing are recommended.

NFPA Standard 701/2019 Edition Test Method 1 & 2 Flammability:

Other Tests Passed: ATSM D3335 85a Lead Test

UL GreenGuard Gold Certified

										SC (Sirigle Glass)			oc (ilibulating Glass)		
No.	Description	Ts	<u>Rs</u>	<u>As</u>	Tv	Rv	<u>Av</u>	<u>Tv</u>	<u>O-F</u>	<u>1/8" CI</u>	<u>1/4" CI</u>	<u>1/4" H.A</u>	<u>1/2" CI</u>	<u>1" CI</u>	<u>1" H.A.</u>
11	White 4 Ply	Tr	79	21	Tr	67	33	Tr	0.2	0.19	0.21	0.25	0.19	0.22	0.2



PHONE







SC (Single Class)



SC (Inculating Class)

Revised 1/2020